



Global Automotive Window Films

Product	Film Construction	Color	Adhesive	# of Plies	Thickness	Warranty*	VLT ¹	Glare Reduction ¹	UV Rejection ¹	Total Solar Energy Rejected ¹	VLT (Measured out of Box) ²	VLT (Measured on Auto 75 Glass) ²
NR Quick Dry Plus												
NR Quick Dry Plus 5%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	6%	93%	99%	42%	7%	6%
NR Quick Dry Plus 15%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	16%	82%	99%	41%	17%	14%
NR Quick Dry Plus 20%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	19%	79%	99%	40%	20%	17%
NR Quick Dry Plus 30%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	30%	67%	99%	35%	30%	25%
NR Quick Dry Plus 35%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	35%	62%	99%	34%	37%	31%
NR Quick Dry Plus 40%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	39%	57%	99%	33%	39%	33%
NR Quick Dry Plus 45%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	45%	51%	99%	32%	46%	37%
NR Quick Dry Plus 50%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	49%	46%	99%	30%	51%	42%
NR Quick Dry Plus 55%	Dyed	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	55%	40%	99%	29%	56%	46%
HP Charcoal Premium												
HP Charcoal Premium 5%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	5%	94%	99%	61%	4%	3%
HP Charcoal Premium 10%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	10%	89%	99%	53%	13%	11%
HP Charcoal Premium 20%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	20%	78%	99%	51%	21%	17%
HP Charcoal Premium 30%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	28%	69%	99%	43%	31%	26%
HP Charcoal Premium 40%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	39%	57%	99%	41%	42%	35%
HP Charcoal Premium 45%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	44%	52%	99%	39%	48%	40%
HP Charcoal Premium 50%	Hybrid	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	54%	41%	99%	34%	58%	48%
QDP Ceramic												
QDP Ceramic 5%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	4%	96%	99%	66%	6%	5%
QDP Ceramic 18%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	18%	80%	99%	62%	21%	18%
QDP Ceramic 33%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	32%	65%	99%	58%	32%	26%
QDP Ceramic 38%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	38%	58%	99%	56%	35%	29%
QDP Ceramic 42%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	42%	54%	99%	53%	39%	32%
QDP Ceramic 46%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	46%	49%	99%	52%	48%	40%
QDP Ceramic 50%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	51%	44%	99%	51%	54%	45%
QDP Ceramic 70%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	69%	24%	99%	47%	72%	60%
QDP Ceramic 80%	Ceramic	Charcoal	Pressure Sensitive	2 plies	2.0 mils	Lifetime	78%	14%	99%	42%	51%	67%
QDP Ceramic 86%	Ceramic	Charcoal	Pressure Sensitive	2 plies	1.5 mils	Lifetime	86%	6%	99%	27%	87%	72%

*Please see warranty for specific terms and conditions.

¹Tested on 1/8" (3mm) clear glass per BS EN 410 standard.

²Tested per ASTM D1003 standard.

³Tested on Auto 75 glass (average of both Green and Gray tinted glass types) per ASTM D1003 standard.